

#### DESCRIPTION

This system describes how a model (or plug) for the production of a polyester mould and produced from a polyurethane foam core, may be coated with a high gloss two component polyurethane system.

#### PRINCIPAL CHARACTERISTICS

This system may be applied to a model (or plug) made from a polyurethane foam core. The system is scratch resistant, and is resistant against various chemicals and solvents, including styrene. The system has an excellent gloss and colour retention.

#### SUBSTRATE CONDITIONS

Polyurethane foam core, sanded with grit paper P180, dry, free from any contamination and in good condition.

#### SURFACE PREPARATION

1. The surface should be completely dry and free from grease (moisture content maximum 12%);
2. Grit paper the surface with grit paper P180 after any spot repair;
3. Thoroughly remove all dust and residue from the surface.

#### MATERIALS AND SPREADING RATE

The following materials are used in the paint system:

Poltix Smitplamuur	spreading rate approx. 0,5 l/m <sup>2</sup>
Double Coat	spreading rate approx. 0,2 kg/m <sup>2</sup>
Double Coat Smitverdunner	spreading rate depends on application method, see additional information
Poltix Ethylacetaat	spreading rate depends on application method

#### APPLICATION

1. Repair damaged areas and joints with Poltix Superplamuur or IJmofix;
2. Apply one coat Poltix Smitplamuur to a total dry film thickness of 350 µm (minimum spreading rate approx. 0,5 l/m<sup>2</sup>);
3. Apply three coats Double Coat to a total dry film thickness of 90 µm (minimum spreading rate approx. 0,2 kg/m<sup>2</sup>);

#### ADDITIONAL INFORMATION

- Polyurethane foam core  
In general a polyurethane foam core has an excellent resistant to styrene. Combined with good sanding properties polyurethane foam core is very suitable for smaller models. The spreading rate of the filler depends on the density of the foam core: less filler will be required for a more dense foam. Larger models or models with joints may be treated with polyester resin in combination with a chopped strand glass fibre., i.e. Poltix Lamineerhars and Poltix Glasmat 225.

This paint system is resistant to the most commonly used solvents in the polyester industry. When the paint system is not resistant to the solvents used in the polyester industry, surface defects may occur during the production of the mould. These defects may be visible in both model and mould as spots with lower gloss, craters and cracks.

## MODELS – POLYURETHANE FOAM CORE

- **Repair of polyurethane foam core**  
Damages to the foam core may be repaired with a filler. Any damage of the foam core should be repaired.  
Suitable fillers are:
  - Poltix Super Plamuur (grey, fast curing, easy to sand, slight shrinkage);
  - IJmofix (white, fast curing, fine filler, easy to sand, slight shrinkage);
- **Durability and surface preparation**  
The durability of any paint system depends on a number of variables, amongst others: total dry film thickness, method of application, skill of labour, the conditions during which the coating is applied and cured, the exposure conditions during service and the preparation of the surface. Insufficient surface preparation might lead to blistering and loss of adhesion.
- **Sanding**  
A durable adhesion will be obtained by thorough preparation of the surface. This may be achieved by sanding the surface. Sanding is also necessary when the time between application of each coat exceeds the maximum overcoating interval.  
During application of the finishing coats, we recommend to use for each coat a finer grit paper.
- **Application of Double Coat**  
Double Coat may be replaced with Double Coat Modellak. Double Coat Modellak is fully cured after 24 hours and is recommended when the model is exposed to the gelcoat the following day. Double Coat Modellak is fast curing and recommended for spray application to smaller models.  
For spray application Double Coat Spuitverdunner may be replaced by Double Coat Spuitverdunner 60. Depending on the model, Double Coat Spuitverdunner 60 will result in less overspray and better levelling.
- **Production of the mould**  
The model (plug) should be allowed to cure at least 5 days after application of the final coat of Double Coat. Apply several layers of release agent; a suitable release agent is Mirroglaze TR88 or equivalent. Buff the release agent thoroughly.
- **Forced curing**  
Avoid forced curing of the paint system as much as possible. Forced curing might result in surface defects in the tooling paste. This will affect the surface quality of the mould negatively.
- **Example working schedule**

Step	Activity	Dry film thickness (µm)	Spreading rate (m <sup>2</sup> /l)	Recoating interval at 20 °C	Preparation before next step
1	Surface pre-treatment				
2	Repair with suitable filler	n.a.	n.a	8 hours	Sanding with P180.
3	Apply Poltix Spuitplamuur	350	2,0	8 hours	Sanding with P180-P240-P320.
4	Apply first coat Double Coat	30	14,3	24 hours	When recoated within 48 hours no preparation required, otherwise sanding with P320-P400. Use between each layer finer grit paper to avoid scratches.
5	Apply second coat Double Coat	30	14,3	24 hours	
6	Apply third coat Double Coat	30	14,3	24 hours	After 5 days production of mould may start. Apply several layers mould release agent first.

For detailed information on the products mentioned in this sheet, please refer to our technical information sheets.

Date: October 18

*Disclaimer*

*The information in this data sheet is based on thorough research and development in combination with practical experience, is to the best of our knowledge and correct at the date of printing. De IJssel Coatings BV does not accept any liability as the final result depends on a number of factors beyond our control, amongst others, but not limited to, skill of labour, application conditions and surface preparation. De IJssel Coatings BV reserves the right to change data without prior notice. This data sheet supersedes all previous issues.*